



Epoxy.com Product #216

Two Component Coal Tar Epoxy Coating

GENERAL DESCRIPTION

DESCRIPTION:

Epoxy.com Product #216 Coal Tar Epoxy is a two component coal tar epoxy coating, black in color, used to protect steel, concrete structures, timber, and other construction materials in corrosive environments. It meets all requirements of Corp. of Engineers C-200, Federal Specification DOD-P-23236 (SHIPS), and SSPC 16-91.

ADVANTAGES:

Epoxy.com Product #216 Coal Tar Epoxy is manufactured in a convenient 1:4 ratio, "A" to "B", and can be applied to steel, concrete, timber, or to other construction materials. To meet the above referenced specifications, two coats are recommended at 10 mils wet film thickness or 8 mils dry film thickness. The cured coating is flexible and affords excellent resistance to impact, thermal shock and abrasion. It cures to a hard, smooth surface, possesses exceptional resistance to immersion in salt water, or in water where an altered pH condition is present.

WHERE TO USE:

Recommended for coating of tanks, piping, sheet piling, foundation walls and sumps. Also suitable for concrete and steel surfaces in sewage treatment plants, paper mills and chemical plants. Excellent for below grade surfaces.

PHYSICAL PROPERTIES:

Solids	84%
Pot Life	4 Hours @ 72° F
Dry Time	@ 72° F
Tack Free	4 - 6 Hours
Handle	6 - 12 Hours
Recoat	16 - 24 Hours
Shelf Life	2 Years
Resin Type	Epoxy Polyamide

SURFACE PREPARATION:

Concrete - For best results on concrete, light sandblasting or other suitable surface preparation is recommended. Compressed air is used to remove residual dust. Any compressed air should be oil free. Apply only to dry surfaces.

Steel - Steel surfaces which are to receive **Epoxy.com Product #216 Coal Tar Epoxy Coating** should be prepared by abrasive blasting to a commercial gray metal (SP-6) standard. Any surface blasted should be coated the same day. If prepared surfaces are contaminated by rust or other contaminants, they must be reblasted.

MIXING:

Add entire contents of "A" Component to "B" Component. Mix with 1/2" slow speed drill (300 to 600 rpm) with **Epoxy.com MIXING PADDLE** for a minimum of three (3) minutes. The 1 "A" : 4 "B" permits mixing of small quantities as long as the ratio is maintained. Let the mixed "A" & "B" stand 10 minutes before application.

APPLICATION:

For best results, apply two (2) coats of **Epoxy.com Product #216** by brush, roller or spray. If spray applied, airless-type equipment is preferred. First coat should be applied at a thickness of approximately 10 mil and allowed to cure tack-free. Second coat should be applied at a rate of approximately 10 mil within 72 hours. If longer delay occurs, scrub first coat with MIBK, and wipe dry with clean cloth before applying second coat.

COVERAGE:

At an 8 mil dry film thickness, one gallon of **Epoxy.com Product #216** will cover approximately 160 square feet per gallon.

PACKAGING:

Packaged for convenient mixing. Available in 5 gallon units. Six gallon pail contains 4 gallons of Component "B" in bottom of pail with 1 gallon of Component "A" on top. The slightly larger containers permit sufficient room for mixing in the can without spilling. Special orders can be packaged in 55 gallon drums.

CAUTION:

DANGER! FLAMMABLE! Contain Xylene. Keep away from heat, sparks and flame. Avoid breathing vapor. Use with forced air ventilation in confined areas. Avoid contact of resin or hardener with the skin or eyes. In case of skin contact, remove with soap and water or waterless hand cleaner. In case of eye contact, flush immediately with plenty of water and consult a physician. Do not take internally.

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.

Many of our products are made on an individual order basis. Unless authorized in writing by Epoxy.com a division of Epoxy Systems, Inc. in writing before the material is made, there are no returns on items purchased from us, once the order has been processed, and the material made. In the event of authorized returns a restocking charge will be charged in the amount of 30% of the value of the material returned or \$150 whichever is greater. No returns on non-list priced items. All Returns are for merchandise (store) credit only, no cash or credit card credits. In the event of a return, buyer is responsible for the cost of shipping and handling in both directions.