



Epoxy.com Product #220

Epoxy Rebar Touch Up Coating

DESCRIPTION

Epoxy.com Product #220 Epoxy Rebar Touch Up Coating, is a two component, 70% solids epoxy coating specially manufactured to touch up damage epoxy coated rebar or to coat rebars not previously protected against corrosion.

ADVANTAGES

Product #220 Epoxy Rebar Touch Up Coating can be field applied. For best results apply at temperatures of 50°F and rising.

PHYSICAL PROPERTIES

Color	Green (other colors available upon request)
Weight per gallon	10 lbs.
Viscosity	3000 cps
Solids	70% by weight
Shelf Life closed container	12 months
Pot Life	8 hours
Drying time at 70°F	Overnight
Closed cup flash point	
Part A	76°F (24°C)
Part B	88°F (31°C)

SURFACE PREPARATION

Surfaces to receive **Epoxy.com Product #220 Epoxy Rebar Touch Up Coating** should be dry and free of oil, grease, dust, scale, rust and damaged coating.

MIXING

Stir Components "A" and "B" thoroughly before mixing. Combine one part by volume of "A" with one part by volume of "B" (mixing ratio 1:1). Mix for not less than three minutes, using a slow speed drill, (300 to 600 rpm) and an **Epoxy.com Mixing Paddle**. When mixing has been completed, cover mixed material and allow an induction time of not less than 45 minutes before application?

APPLICATION

Product #220 Epoxy Rebar Touch Up Coating can be applied by brush or roller.

COVERAGE

Epoxy.com Product #220 Epoxy Rebar Touch Up Coating when applied at an approximate rate of 300 square feet per gallon will provide a film thickness of 5.25 mils wet and 3.75 mils dry. Two (2) coats are recommended

PACKAGING

Epoxy.com Product #220 Epoxy Rebar Touch Up Coating is packaged in two (2) gallon and ten (10) gallon units.

CAUTION

"A" Component: May cause skin sensitization or other allergic responses. Avoid inhalation of vapor. Use good ventilation, particularly if material is heated or sprayed. Prevent all contact with skin or eyes. Wear protective clothing, goggles, gloves and/or barrier cream. If contact with skin occurs, wash immediately with soap and water. In case of contact with eyes, flush immediately with water and contact a physician.

CAUTION! DANGER! Contains alkaline amines; strong sensitizer. Do not get into eyes, on skin or clothing. Avoid breathing vapor. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

FIRST AID

In case of contact, immediately flush eyes or skin with plenty of water for at least 15 minutes. Remove contaminated clothing and shoes. Call a physician. Wash clothing before reuse. Discard contaminated shoes. Wear protective clothing, goggles, gloves and/or barrier creams.

FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.