

# EpoxySystems' Product #426 Urethane Injection Resin Accelerator

#### **DESCRIPTION**

**EpoxySystems' Product #426 Urethane Injection Resin Accelerator** is specifically formulated to increase the cure rate of **EpoxySystems' Product #4 Urethane Injection Resin**. The accelerator liquid is normally used to compensate for cold weather or cold water temperatures.

#### **HOW TO USE**

**EpoxySystems' Product #426 Urethane Injection Resin Accelerator** is added to the mixing water at a rate of 11.5 fluid ounces of accelerator to 20 gallons of mixing water. Rinse accelerator container with water to completely empty container.

#### PHYSICAL PROPERTIES

| Color       | Clear               |
|-------------|---------------------|
| Weight      | 8.1 lbs. per gallon |
| Flash Point | 255°F               |

#### **CURE TIME**

| Temperature | Water   | Water with Accelerator |
|-------------|---------|------------------------|
| 40°F        | 15      | 5.5 mins.              |
|             | mins.   |                        |
| 70°F        | 8 mins. | 3.5 mins.              |
| 100°F       | 5 mins. | 2.5 mins.              |

#### **CAUTION**

Danger Contains amine compounds. Avoid contact with skin and avoid breathing vapors. Wear rubber gloves and goggles to protect skin and eyes. In case of skin contact wash thoroughly with soap and water. In case of eye contact flush immediately with water and contact a physician. Use in well ventilated areas.

## FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

For more information please contact:

### **Epoxy Systems, Inc.**

Jericho, Vermont 05465 (802) 899-2844 (voice) (802) 899-3843 (fax) info@epoxy.com (Internet) www.epoxy.com (WWW)

This information is presented in good faith to assist the user in determining whether our products are suitable for application. No warranty or representation, however, is intended or made, nor is protection from any law or patent to be inferred, and all patent rights are reserved. 0501