



Epoxy Systems' Product #636

Amine Cured 100% Solids Primer and Topcoat

DESCRIPTION

Epoxy Systems' Product #636 is a 100% solids amine cured epoxy Novolac that is solvent free. Specifically designed as a Methanol resistant coating. Product #635 is well suited for use in a wide array of aggressive acids, alkalies and organic solvents. **Epoxy Systems Product #636** produces a tough, chemical resistant coating on concrete, iron and non-iron surfaces. As a low viscosity epoxy Novolac it is suitable for hand or spray application.

USES

- Methanol Pumps
- Tanks
- Pipes
- Aggressive Chemical Tank Linings,
- Secondary Chemical Containment Areas
- Industrial Flooring

NO LONGER AVAILABLE - CONTACT TECH SUPPORT

ADVANTAGES

- Exhibits excellent resistance to Methonol, and a host of strong acids, alkalis, and organic solvents
- High build yields a durable surface
- Can be applied in occupied facilities
- Can be used in immersion service up to 350 degrees F. (177 degrees C) with a spike (3 hour) temperature of up to 400 degrees F. (204 degrees C) with recommended force cure for 6 hours at 200 degrees F. (94 degrees C).
- 3 year shelf life at 55-95 degrees F, 13-35 degrees C..

CONSIDERATIONS

- Concrete substrate must be free of dirt, waxes, curing agents, and other foreign materials.
- Steel surfaces must be free of grease and oils. Abrasive blast, required for steel.

PHYSICAL PROPERTIES	
Color	Red, other colors by special order only
Solids Content	100%
Viscosity	50,000-70,000 CPS
Mix Ratio	2A to 1B by volume
Pot Life	20 minutes / gal @ 72 degrees F.
VOC	0%

CHEMICAL RESISTANCE PROPERTIES	
Water	Excellent
Alkalies	Excellent
Inorganic Acids	Excellent
Organic Acids	Good
Organic Solvents	Excellent

DRY TIME	
Foot Traffic	8-12 hrs
Recoat @77 Degrees F.	6 - 14 hrs.
Immersion Service	7 days

APPLICATION

SURFACE PREPARATION

Steel Surfaces should be blasted to an SSPC SP6 commercial gray metal blast. Immersion applications should be blasted to an SSPC SP-5 white metal. Grind flat all burrs, weld seams, round sharp edges. Freshly blasted surface can be primed with this material.

Concrete surfaces should be abrasive clean to remove soft surfaces, paint, sealers, and any other contamination. Prime with Epoxy Systems #12 primer or neat #636, or #637.

INSTALLATION

Mix 2 Parts Resin (A) to 1 part Hardener (B) by volume, adding the B to the A. Mix with a mixing stick or low speed drill with a mixing paddle. Do not thin.

Apply by brush, roller, or airless spray. To brush use medium to stiff bristle brush with a bristle quality that does not pull out into the coating. To roll use a 1/8 to 1/4 inch nap roller on concrete. To plural spray use .019 - .021 tip at 2,000-2,500 PSI. Heat "A" component to 120 degrees F. Heat "B" to 110 degrees F. To spray by airless spray, use .019-.023 tip at 2,000-2,500 psi with in line heater only (Caution: Short pot life). It is not recommended that you use conventional spray. Apply two coats at 10 mils thick each for dry applications. A third coat for a total thickness of 30 mils recommended for immersion applications.

Keep material between 55 degrees F and 95 degrees F. Maintain a substrate temperature between 45 and 105 degrees F. The difference in temperature between the substrate and the coating should never exceed 10 degrees F.

For best chemical and temperature resistance force cure for 12 hours at 150 degrees F, 6 hours at 250 degrees F.

Application thickness should be 20 mils (.51mm) / coat. For immersion service use 2-3 coats.

NO LONGER AVAILABLE

WARRANTY

Epoxy Systems, Inc. ("ESI") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of ESI. If any product fails to meet this warranty, the liability of ESI will be limited to replacement of any non-conforming material if notice of such non-conformity is given to ESI within (1) one year of delivery of materials, ESI may in its discretion refund the price received by ESI in lieu of replacing the material. No customer, distributor, or representative of ESI is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of ESI. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. ESI reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. ESI'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND ESI SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

More information

For more information about this product or any other Epoxy Systems' product, please contact:

Epoxy Systems, Inc.

Dunnellon, FL 34431
(352) 489-1666 (Voice)
(352) 465-3497 (Fax)

info@Epoxy.com (Internet)
www.Epoxy.com (WWW)

This information is presented in good faith to assist in determining whether this product is suitable for application. No warranty or representation, however, is intended or made, nor is protection from any law or patent to be inferred, and all patent rights reserved.